



**GENERAL SPECIFICATIONS  
BITUMEN 60/70**

	TEST	UNIT	LIMITS	
DEN@15DEGC	ISO 3675	Kg/L	MIN 0.94	MAX 0.97
VIS@50DEGC	ISO 3104	CST		MAX 300
SUL	ISO 8754	% (M/M)		MAX 3.5
POUR	ISO 3016	DEGC		MAX 4
WATER	ISO 3733	% (V/V)	REPORT	
CCR	ASTM D4530	% (M/M)		MAX 14
ASPHALTENES	IP143	% wt	MIN 6	
ASH	ASTM D482	% (M/M)		MAX 0.15